ELSAYAAD MINING

Pioneers in Egypt’s Calcium Carbonate Industry

TECHNICAL DATA SHEET

Uncoated Ground Calcium Carbonate

GRADE U008 | TYPICAL VALUES

Particle-size distribution
D97 8 ± 0.5 µm
D50 2±0.2 µm
Particles below 2 µm 47-52 %

Physical and treatment properties
Brightness (RY) 97.5±0.5 %
Yellow index 2.5 Max %
Loose bulk density 0.55±0.05 gm/100cm³
Oil absorption 20.2±0.5 g/100 g

Chemical composition
$CaCO_3$ 99.8%
CaO 55.6%
MgO 0.15%
Fe_2O_3 0.003%
Al_2O_3 0.002%
SiO_2 0.01 - 0.03%
Loss on Ignition 44.02%

General properties
Refractive index 1.59
pH 9 max
Hardness (Mohs) 3
Moisture 0.2% max
PSD method Malvern

Confirm final specifications, packing and lot results for each order.

ELSAYAAD MINING | MINYA, EGYPT

LOCAL SALES
info@elsayaadmining.com

EXPORT SALES
export@elsayaadmining.com